

FAST DRYING RED OXIDE

RAW MATERIAL	QTY IN WEIGHT (Kg)
Synthetic Red Oxide	10.00
Zinc Octate (6%)	1.00
Aluminum Stearate (Hi Gel)	1.00
Whiting Chalk (PBR)	20.00
China Clay (500 Mesh)	10.00
Soyalecithine	0.50
ACRY – 25 50%	35.00
Xylene	22.00
Zirconium Octate (18%)	0.35
Cobalt Octate (6%)	0.15
Total	100.00

DRYING TIME

Surface Dry	1 – 2 Minutes
Tack Free	4 – 5 Minutes
Hard Dry	2 Hours
Gloss Level at 60 Degree	Matt

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
Synthetic Red Oxide	Sudarshan Chemical	Pigment
Aluminum Stearate (Hi Gel)	IRRH Specialty	Anti-Settling Agent
Whiting Chalk (PBR)	20 Microns	Extender
China Clay	20 Microns	Minerals
Soyalecithine	Soya Products	Dispersing Agent
Zirconium Octate (18%)	Alpha Chemie	Drier
Cobalt Octate (6%)	Alpha Chemie	Drier



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006