

AUTO REFINISH WHITE

| RAW MATERIAL | QTY IN WEIGHT (Kg) |
|------------------------|--------------------|
| TiO2 Rutile | 19.00 |
| Sunstab Solution (25%) | 0.19 |
| Zinc Octate (6%) | 0.47 |
| Calcium Octate (3%) | 0.75 |
| F – 4092 55% | 68.00 |
| Xylene | 10.10 |
| Zirconium Octate (18%) | 0.95 |
| Cobalt Octate (6%) | 0.38 |
| MEK Oxime (100%) | 0.16 |
| Total | 100.00 |

PROPERTIES

| | | |
|---|-----------------|------------|
| Sp. Gravity | 1.13 ± 1% | |
| HG | 6 – 7+ | |
| Viscosity at 30°C Temperature in Ford Cup B-4 | 100 ± 10 Second | |
| Drying Time | Touch Dry | 5 Minutes |
| | Tack Free | 45 Minutes |
| | Hard Dry | Over Night |
| Gloss Level at 60 Degree | 90 | |

RAW MATERIAL DATA

| Raw Material | Supplier Name | Purpose of Use |
|------------------------|----------------|---------------------|
| TiO2 Rutile | Dupont | Pigment |
| Sunstab Solution | Alpha Chemie | Dispersing Agent |
| Zinc Octate (6%) | Alpha Chemie | Drier |
| Calcium Octate (3%) | Alpha Chemie | Drier |
| Cobalt Octate (6%) | Alpha Chemie | Drier |
| MEK Oxime | Dura Chemicals | Anti-Skinning Agent |
| Zirconium Octate (18%) | Alpha Chemie | Drier |



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006