

HAMMER TONE SILVER

RAW MATERIAL	QTY IN WEIGHT (Kg)
Non Leafing Aluminum Paste	4.00
MFHF 70%	65.21
Xylene	30.19
Cobalt Octate (6%)	0.50
M-Three Lac Solution 10%	0.10
Total	100.00

PROPERTIES

Sp. Gravity	0.98 ± 3%
Viscosity at 30°C Temperature in Ford Cup B-4	85 ± 5 Second

***Note: For Lead Free formulation use Zirconium Octate (6%) as 2.80 Kg**

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
Non Leafing Paste	Sudarshan Chemical	Pigment
Cobalt Octate (6%)	Alpha Chemie	Drier
M Three Lac Solution	Wacker	Hammer Finish



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802

E-mail : mkt@macropolymers.com Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006