

AUTO REFINISH BLACK

RAW MATERIAL	QTY IN WEIGHT (Kg)
C Black FW 200	2.00
BYK ATU	0.20
TPA – 2001 50%	40.00
NC 30/50 (20% Solution)	10.00
Butyl Acetate	27.80
Xylene	20.00
Total	100.00

PROPERTIES

Drying Time	Surface Dry	5 Minutes
	Tack Free	15 Minutes
	Hard Dry	Over Night
DFT/Coat	20 – 25 Micron	

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
C. Black FW	Degussa	Pigment
BYK ATU	BYK	Wetting & Dispersing
NC – 30/50	Nitrex	Binder



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006

AUTO REFINISH WHITE

RAW MATERIAL	QTY IN WEIGHT (Kg)
TiO2 Rutile	17.00
Zinc Oxide	1.00
W&D – 4070	0.20
K – 654	0.15
TPA – 2001 50%	58.00
Xylene	23.25
Antil – 369	0.20
Anchor – 252	0.20
Total	100.00

PROPERTIES

Sp. Gravity	1.07 ± 3%
HG	7+
Viscosity at 30°C Temperature in Ford Cup B – 4	85 ± 10 Second

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
TiO2 Rutile	Dupont	Pigment
Zinc Oxide	IRRH Specialty	Minerals
W&D – 4070	K-Tech	Wetting & Dispersing Agent
K – 654	K-Tech	Defoamer
Antil – 369	K-Tech	Adhesion Promoter
Anchor – 252	K-Tech	Adhesion Promoter



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006