

# CONCRETE COATING WHITE

RAW MATERIAL	QTY IN WEIGHT (Kg)
TiO2 Rutile	18.00
Zinc Oxide	3.00
BYK – 190	0.10
TPA – 696 60%	25.00
CAB 551-05 (20% Solution in Butyl Acetate)	5.00
Butyl Acetate	25.00
Xylene	23.90
<b>Total</b>	<b>100.00</b>

## PROPERTIES

Drying Time	Surface Dry	15 Minutes
	Tack Free	20 Minutes
	Hard Dry	Over Night
DFT/Coat		20 – 25 Micron

## RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
TiO2 Rutile	Dupont	Pigment
Zinc Oxide	IRRH Specialty	Minerals
BYK – 190	BYK	Dispersing Additive
CAB-551-05	Eastman	Binder



ISO 9001:2008



### Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802  
E-mail : [mkt@macropolymers.com](mailto:mkt@macropolymers.com) Website : [www.macropolymers.com](http://www.macropolymers.com)  
CIN : U17119GJ1994PTC024006