

2K EPOXY FINISH GOLDEN YELLOW

BASE

RAW MATERIAL	QTY IN %
Middle Chrome	25.00
PAT DA – 1666	0.20
Modaflow Resin	0.50
CR – 250 100%	42.00
Xylene	20.00
n-Butanol	9.10
BYK – 410	0.20
Cellosolve Acetate	3.00
Total	100.00

HARDENER COMPONENT

RAW MATERIAL	QTY IN %
Polyamide SP – 160 100%	95.00
Macmine – 03	5.00
Total	100.00

MIXING RATIO

RAW MATERIAL	QTY BY VOLUME
Base	4.00
Hardener	1.00



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006

PROPERTIES

Drying Time	Surface Dry	1 – 2 Hour
	Tack Free	6 – 8 Hours
	Hard Dry	24 Hours
Full cure	7 Days	
Pot Life	3 – 5 Hours	
Salt Spray Test	500 Hours Pass	

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
Middle Chrome	Sudarshan Chemical	Pigment
PAT ADD DA – 1666	Patcham	Dispersing Agent
Modaflow Resin	Cytec	Leveling Agent
BYK – 410	BYK	Rheology Additive
CR – 250	Macro Polymers	Binder
Macmine-03	Macro Polymers	Accelerator



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006