

# PU BASE SEALER

## BASE

RAW MATERIAL	QTY IN WEIGHT (Kg)
C – 1030 70%	39.00
Zinc Stearate	3.00
Talc	12.00
Fine Silica – 1240	12.00
Bentec P – 2	1.00
Xylene	20.00
Butyl Acetate	9.00
Ethyl Acetate	4.00
<b>Total</b>	<b>100.00</b>

## ACTIVATOR COMPOUND

RAW MATERIAL	QTY IN WEIGHT (Kg)
Desmodur L – 75	65.00
Xylene	25.00
Butyl Acetate	10.00
<b>Total</b>	<b>100.00</b>

## MIXING RATIO

RAW MATERIAL	RATIO BY VOLUME
Base	15.00
Activator Compound	5.00



ISO 9001:2008



### Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802  
E-mail : [mkt@macropolymers.com](mailto:mkt@macropolymers.com) Website : [www.macropolymers.com](http://www.macropolymers.com)  
CIN : U17119GJ1994PTC024006

## PROPERTIES

Drying Time	Touch Dry	10 – 15 Minutes
	Tack Free	60 ± 10 Minutes
Sanding Time		60 – 70 Minutes

## RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
Zinc Stearate	IRRH Specialty	Minerals
Talc	20 Microns	Minerals
Fine Silica – 1240	20 Microns	Minerals
Bentec P – 2	Bentec	Anti-Settling Agent
Desmodur L – 75	Bayer	Aromatic Poly-Isocyanate



ISO 9001:2008



### Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802  
E-mail : [mkt@macropolymers.com](mailto:mkt@macropolymers.com) Website : [www.macropolymers.com](http://www.macropolymers.com)  
CIN : U17119GJ1994PTC024006

## NC PAINT RED

RAW MATERIAL	QTY IN WEIGHT (Kg)
Toludine Red – 415	5.00
PAT ADD DA – 701	0.50
Zinc Octate (6%)	0.50
DOP	3.00
C – 1030 70%	24.00
Mix Solvent	24.00
NC 30/50 Solution (40%)	43.00
<b>Total</b>	<b>100.00</b>

### MIX SOLVENT RATIO

RAW MATERIAL	QTY IN WEIGHT (Kg)
Toluene	50.00
DAA	5.00
IPA	15.00
Ethyl Acetate	20.00
Butyl Acetate	10.00
<b>Total</b>	<b>100.00</b>

### 40% NC 30/50 SOLUTION RATIO

RAW MATERIAL	QTY IN WEIGHT (Kg)
NC 30/50	40.00
Toluene	30.00
DAA	5.00
IPA	10.00
Ethyl Acetate	10.00
Butyl Acetate	5.00
<b>Total</b>	<b>100.00</b>



ISO 9001:2008



#### Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802  
E-mail : [mkt@macropolymers.com](mailto:mkt@macropolymers.com) Website : [www.macropolymers.com](http://www.macropolymers.com)  
CIN : U17119GJ1994PTC024006

## PROPERTIES

Specific Gravity	0.95 ± 0.03	
HG	6+	
Drying Time	Touch Dry	2 – 5 Minutes
	Tack Free	10 – 15 Minutes
	Hard Dry	30 – 45 Minutes
Gloss Level at 60 Degree	70 - 75	

## RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
Toludine Red – 415	Sudarshan Chemical	Pigment
PAT ADD DA – 701	Patcham	Dispersing Agent
Zinc Octate (6%)	Alpha Chemie	Drier
DOP	India Glycol	Plasticizer
NC 30/50	Nitrex	Binder



ISO 9001:2008



### Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802

E-mail : [mkt@macropolymers.com](mailto:mkt@macropolymers.com) Website : [www.macropolymers.com](http://www.macropolymers.com)

CIN : U17119GJ1994PTC024006