

PU BASE SEALER

BASE

RAW MATERIAL	QTY IN WEIGHT (Kg)
TO – 1300 60%	46.00
Zinc Stearate	3.00
Talc	12.00
Fine Silica – 1240	12.00
Bentec P – 2	1.00
Xylene	13.00
Butyl Acetate	9.00
Ethyl Acetate	4.00
Total	100.00

ACTIVATOR COMPOUND

RAW MATERIAL	QTY IN WEIGHT (Kg)
Desmodur L – 75	65.00
Xylene	25.00
Butyl Acetate	10.00
Total	100.00

MIXING RATIO

RAW MATERIAL	RATIO BY VOLUME
Base	15.00
Activator Compound	5.00



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006

PROPERTIES

Drying Time	Touch Dry	10 – 15 Minutes
	Tack Free	60 ± 10 Minutes
Sanding Time		60 – 70 Minutes

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
Zinc Stearate	IRRH Specialty	Minerals
Talc	20 Microns	Minerals
Fine Silica – 1240	20 Microns	Minerals
Bentec P – 2	Bentec	Anti-Settling Agent
Desmodur L – 75	Bayer	Aromatic Solvent



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006