

1K TOUCH WOOD GLOSSY

RAW MATERIAL	QTY IN WEIGHT (Kg)
TS – 8060 60%	90.00
Zirconium Octate (6%)	1.80
Cobalt Octate (6%)	0.40
Calcium Octate (3%)	2.00
MEK Oxime (100%)	0.20
PAT LE – 1019	0.30
Toluene	5.30
Total	100.00

PROPERTIES

Sp. Gravity	0.95 ± 1%	
Viscosity at 30°C Temperature in ford Cup B-4	120 ± 10 Second	
Drying Time	Surface Dry	5 – 10 Minutes
	Tack Free	30 – 40 Minutes
	Hard Dry	3 – 4 Hours
Gloss Level at 60 Degree	98	

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
Zirconium Octate (6%)	Alpha Chemie	Drier
Cobalt Octate (6%)	Alpha Chemie	Drier
Calcium Octate (3%)	Alpha Chemie	Drier
MEK Oxime (100%)	Dura Chemical	Anti-Skinning Agent
PAT LE – 1019	Patcham	Surface Modifier



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006