

## 2K WOOD FINISH CLEAR

### BASE

RAW MATERIAL	QTY IN %
TSA – 1050 60%	65.80
Xylene	4.80
Butyl Acetate	17.80
AFCONA – 3033	0.20
PMA	11.40
<b>Total</b>	<b>100.00</b>

### HARDENER COMPONENT

RAW MATERIAL	QTY IN %
Desmodur N – 75	62.00
Butyl Acetate	28.00
PMA	10.00
<b>Total</b>	<b>100.00</b>

### RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
AFCONA – 3033	Afcona	Leveling Agent
Desmodur N – 75	Bayer	Aliphatic Poly Isocyanate



ISO 9001:2008



#### Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802  
E-mail : [mkt@macropolymers.com](mailto:mkt@macropolymers.com) Website : [www.macropolymers.com](http://www.macropolymers.com)  
CIN : U17119GJ1994PTC024006