

AUTO REFINISH WHITE

RAW MATERIAL	QTY IN WEIGHT (Kg)
TiO2 Rutile	19.00
Sunstab Solution (25%)	0.19
Zinc Octate (6%)	0.47
Calcium Octate (3%)	0.75
F – 4093 55%	68.00
Xylene	10.10
Zirconium Octate (18%)	0.95
Cobalt Octate (6%)	0.38
MEK Oxime (100%)	0.16
Total	100.00

PROPERTIES

Sp. Gravity	1.13 ± 1%	
HG	6 – 7+	
Viscosity at 30°C Temperature in Ford Cup B-4	100 ± 10 Second	
Drying Time	Touch Dry	5 Minutes
	Tack Free	45 Minutes
	Hard Dry	Over Night
Gloss Level at 60 Degree	90	

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
TiO2 Rutile	Dupont	Pigment
Sunstab Solution	Alpha Chemie	Dispersing Agent
Zinc Octate (6%)	Alpha Chemie	Drier
Calcium Octate (3%)	Alpha Chemie	Drier
Cobalt Octate (6%)	Alpha Chemie	Drier
MEK Oxime	Dura Chemicals	Anti-Skinning Agent
Zirconium Octate (18%)	Alpha Chemie	Drier



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006