

AIR DRYING AUTO REFINISH WHITE

RAW MATERIAL	QTY IN WEIGHT (Kg)
TiO2 Rutile	20.00
Calcium Octate (3%)	1.00
PAT DA - 701	0.30
F - 8169 70%	48.42
Xylene	26.88
Zirconium Octate (6%)	2.80
Cobalt Octate (6%)	0.40
MEK Oxime (100%)	0.20
Total	100.00

PROPERTIES

Sp. Gravity	1.13 ± 1%	
HG	6 - 7+	
Viscosity at 30°C Temperature in Ford Cup B-4	100 ± 10 Second	
Drying Time	Touch Dry	10 - 15 Minutes
	Tack Free	60 - 80 Minutes
	Hard Dry	10 - 12 Hours
Gloss Level at 60 Degree	90	

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
TiO2 Rutile	Dupont	Pigment
Calcium Octate (6%)	Alpha Chemie	Drier
PAT DA - 701	Patcham	Dispersing Agent
Zirconium Octate (18%)	Alpha Chemie	Drier
Cobalt Octate (6%)	Alpha Chemie	Drier
MEK Oxime (100%)	Dura Chemicals	Anti-Skinning Agent



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006