

AUTO REFINISH RED

RAW MATERIAL	QTY IN %
Sudaperm – 415	5.00
BYK – 190	0.20
TPA – 2001M HV	38.00
NC 30/50 (20% Solution)	8.00
Butyl Acetate	20.00
Xylene	21.00
Toluene	7.80
Total	100.00

PROPERTIES

Drying Time	Surface Dry	5 Minutes
	Tack Free	10 Minutes
	Hard Dry	Over Night
DFT/Coat	20 – 25 Micron	

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
Sudaperm – 415	Sudarshan Chemical	Pigment
BYK – 190	BYK	Dispersing Agent
NC – 30/50	Nitrex	Binder



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802
E-mail : mkt@macropolymers.com Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006