

2K AIR DRYING WHITE PAINT

BASE

RAW MATERIAL	QTY IN %
TiO2 Rutile	28.00
Macryl – 7303 60%	57.00
PAT ADD DA - 934	0.14
Zinc Octate (6%)	0.54
PAT AF – 62	0.20
Butyl Acetate	4.40
Xylene	6.10
PMA	2.50
AFCONA – 3033	0.12
1% DBTL Soln	1.00
Total	100.00

HARDNER COMPONENT

RAW MATERIAL	QTY IN %
Desmodur N – 3390	56.00
Xylene	24.00
Butyl Acetate	20.00
Total	100.00

MIXING RATIO

RAW MATERIAL	BY VOLUME
Base	4.00
Hardener Component	1.00



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802

E-mail : mkt@macropolymers.com Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

THINNER COMPOSITION

RAW MATERIAL	QTY IN WEIGHT (Kg)
Xylene	70.00
Butyl Acetate	20.00
Ethyl Acetate	5.00
PMA/Cellosolve Acetate	5.00
Total	100.00

PROPERTIES

Sp. Gravity	0.98 ± 1%	
Drying Time	Surface Dry	10 Minutes
	Tack Free	1 Hours
	Hard Dry	Over Night
Complete Cure	7 Days	
Pot Life	2 – 3 Hours	
DFT/Coat	25 – 30 Microns	
Salt Spray	600 Hours Pass	
QUV Data	Total Hours Pass	1000 Hours
	Gloss 20°	86
	Gloss 60°	98
Gloss Retention after QUV Test	20°	65 After 1000 Hours
	60°	86 After 1000 Hours

RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
TiO ₂	Dupont	Pigment
PAT ADD DA – 934	Patcham	Dispersing Agent
Zinc Octate (6%)	Alpha Chemie	Drier
PAT AF – 62	Patcham	Defoamer
AFCONA – 3033	Afcona	Leveling Agent
1% DBTL Soln	SV Plastochem	Initiator
Desmodur N – 3390	Bayer	Aliphatic Poly Isocyanate



ISO 9001:2008



Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802

E-mail : mkt@macropolymers.com Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006