

# 2K AIR DRYING WHITE PAINT

## BASE

RAW MATERIAL	QTY IN %
TiO2 Rutile	28.00
Macryl – 8218 60%	57.00
PAT ADD DA – 932	0.80
Zinc Octate (6%)	0.53
PAT AF – 62	0.20
Butyl Acetate	4.40
Xylene	5.67
PMA	2.00
AFCONA – 3033	0.40
1% DBTL Soln	1.00
<b>Total</b>	<b>100.00</b>

## HARDNER COMPONENT

RAW MATERIAL	QTY IN %
Desmodur N – 75	60.00
Xylene	21.00
Butyl Acetate	19.00
<b>Total</b>	<b>100.00</b>

## MIXING RATIO

RAW MATERIAL	BY VOLUME
Base	4.00
Hardener Component	1.00



ISO 9001:2008



### Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802  
E-mail : [mkt@macropolymers.com](mailto:mkt@macropolymers.com) Website : [www.macropolymers.com](http://www.macropolymers.com)  
CIN : U17119GJ1994PTC024006

## THINNER COMPOSITION

RAW MATERIAL	QTY IN WEIGHT (Kg)
Xylene	70.00
Butyl Acetate	20.00
Ethyl Acetate	5.00
PMA/Cellosolve Acetate	5.00
<b>Total</b>	<b>100.00</b>

## PROPERTIES

Sp. Gravity	0.96 ± 1%	
Drying Time	Surface Dry	1 Hour
	Tack Free	2 – 3 Hours
	Hard Dry	Over Night
Complete Cure	7 Days	
Pot Life	4 – 6 Hours	
DFT/Coat	25 – 30 Microns	
Salt Spray	600 Hours Pass	

## RAW MATERIAL DATA

Raw Material	Supplier Name	Purpose of Use
TiO <sub>2</sub>	Dupont	Pigment
PAT ADD DA – 932	Patcham	Dispersing Agent
Zinc Octate (6%)	Alpha Chemie	Drier
PAT AF – 62	Patcham	Defoamer
AFCONA – 3033	Afcona	Leveling Agent
1% DBTL Soln	SV Plastochem	Initiator
Desmodur N – 75	Bayer	Aliphatic Poly Isocyanate



ISO 9001:2008



### Corporate & Registered Office :

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91-9898079802  
E-mail : [mkt@macropolymers.com](mailto:mkt@macropolymers.com) Website : [www.macropolymers.com](http://www.macropolymers.com)  
CIN : U17119GJ1994PTC024006