

Date/Rev.:16.03.2024/01

MACROLIC 8540

2K hydroxy functional acrylic copolymer, able to crosslink at room temperature

PRINCIPAL PROPERTIES

- > Excellent adhesion on Non-Ferrous Metal surface
- Good gloss
- > Fast drying

APPLICATIONS

- > Suitable for DTM coating
- > Specially designed for stainless steel, GI, copper, glass & brass
- > Applicable to metal & plastic substrate
- > Auto OEM or refinishes coatings
- Two pack coating for the industrial lacquer sector

PHYSICAL CONSTANTS

Solid % (130°C / 30 min)	60 ± 2
Appearance	Clear
Color (APHA / pt-co)	30 max
Acid Value (On Solid) (mg KOH/gm)	2-10
Viscosity in poise (as such at 25° C on RVDVE with SSA/ Spindle-28/ RPM-100)	15-35
Hydroxyl Value (On Solid) (mg KOH/gm)	40-60

MIXING RATIO

Mixing Ratio can be calculated as below.

OH No. * 7.5 / NCO % = Weight of isocyanate required to cure 100 gm polyol







MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya, Tal. Sanand, Dist.: Ahmedabad-382213. Phone: + 91 7600060933 Website: www.macropolymers.com

CIN: U17119GJ1994PTC024006



SOLUBILITY

Mix Xylene	Soluble
Toluene	Soluble
Butyl Acetate	Soluble

DELIVERY FORM

MACROLIC 8540	$60 \pm 2\%$ in Mix Xylene , Butyl Acetate
---------------	--

SHELF LIFE

2 Years*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.







MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya, Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website: www.macropolymers.com
CIN: U17119GJ1994PTC024006