

MACROLIC AF-50

Thermoplastic Acrylic Resin

PRINCIPAL PROPERTIES

- Excellent antifouling properties
- Self polishes
- Water resistance
- Fast drying
- Good hardness

APPLICATION

- Marine & protective coating

PHYSICAL CONSTANTS

Solid % (120°C / 1 hr)	50 ± 2
Appearance	Clear
Colour on Gardner scale	6 max
Acid Value (On Solid) (mg KOH/gm)	45-60
Viscosity in poise (as such at 25°C in B.F. LVT Spindel - 3 / RPM - 12)	1-5

SOLUBILITY

Mix Xylene	Soluble
Butyl Acetate	Soluble
Toluene	Soluble



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

DELIVERY FORM

MACROLIC AF-50	$50 \pm 2\%$ in Aromatic solvents , PMA
----------------	---

SHELF LIFE

2 Years*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.

**MACRO POLYMERS PVT. LTD.**

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006