

MACROLIC TPA-7626 LV

Thermoplastic Acrylic Resin

PRINCIPAL PROPERTIES

- Very good weathering & alcohol resistance
- Excellent flexibility
- Pigment dispersion properties and plasticizer resistance
- High gloss and good gloss retention
- Excellent yellowing resistance
- Excellent hardness
- Very good exterior durability
- Low odour type

APPLICATION

- Can be used for aluminum paste orientation
- Automotive finishes
- Metallic shades in air drying systems

PHYSICAL CONSTANTS

Solid % (120°C / 1 hr)	50 ± 2
Appearance	Clear
Colour (APHA / pt-co)	20 max
Acid Value (On Solid) (mg KOH/gm)	2 max
Viscosity in poise (40% in mix xylene at 25°C in B.F. RVT S.S.A. Spindel - 28 / RPM - 100)	5-25

SOLUBILITY

Mix Xylene	Soluble
Butyl Acetate	Soluble
Toluene	Soluble



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

DELIVERY FORM

MACROLIC TPA-7626 LV	50 ± 2% in Mix Xylene , Toluene
----------------------	---------------------------------

SHELF LIFE

2 Years*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.

**MACRO POLYMERS PVT. LTD.**

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006