

MACROLIC TSA-1001 M

Thermosetting Acrylic Resin

PRINCIPAL PROPERTIES

- Good gloss & color retention
- Good hardness & flexibility
- Good chemical & stain resistance
- Good polishing property
- Better outdoor durability

APPLICATIONS

- For domestic appliance coating
- Low bake stoving paints
- Lacquers for automotive

PHYSICAL CONSTANTS

Solid % (120°C / 1 hr)	60 ± 2
Appearance	Clear
Color (APHA / pt-co)	50 max
Acid Value (On Solid) (mg KOH/gm)	15 max
Viscosity in poise (as such at 25° C in B.F. RVT S.S.A. Spindel - 28 / RPM - 100)	10-20

**MACRO POLYMERS PVT. LTD.**

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

SOLUBILITY

Mix Xylene	Soluble
Toluene	Soluble
Butyl Acetate	Soluble

DELIVERY FORM

MACROLIC TSA-1001 M	60 \pm 2% in Mix Xylene , N-Butanol
---------------------	---------------------------------------

SHELF LIFE

2 Years*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.

**MACRO POLYMERS PVT. LTD.**

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006