

MACRKYD F-4092

Short Oil Pentaerythritol Esterified Chain Stop Alkyd Resin modified with Soyabean Fatty Acid

PRINCIPAL PROPERTIES

- Fast Air drying
- Good recoat ability
- Excellent gloss and gloss retention
- Good surface and through drying
- Good adhesion on metal surface

APPLICATIONS

- Auto refinish
- Baking paints
- Fast drying industrial finishes
- Making of heavy duty primers
- Scaffolding finish

PHYSICAL CONSTANTS

Solid % (120°C / 3 hr)	55 ± 2
Appearance	Clear
Colour on Gardner scale	10 max
Acid Value (On Solid) (mg KOH/gm)	15 max
Viscosity in poise (as such at 25°C in B.F. RVT S.S.A. Spindel - 28 / RPM - 60)	40-60



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

SOLUBILITY

Mix Xylene	Soluble
Butyl Acetate	Soluble
N-Butanol	Insoluble
Toluene	Soluble
MTO / W.S.	Insoluble

COMPATIBILITY

MACRO POL PB-260 (100%)	Compatible
UF Resin	Compatible
MF Resin	Compatible
MACOXY ESTER 3560 (60%)	Not Compatible
MACRO POL MRGLY (100%)	Compatible

DELIVERY FORM

MACRKYD F-4092	55 ± 2% in Mix Xylene
----------------	-----------------------

SHELF LIFE

2 Years*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006