

MACRKYD F-4038

Short Oil Pentaerythritol Esterified Chain Stop Alkyd Resin modified with Soyabean oil type Fatty Acid

PRINCIPAL PROPERTIES

- Excellent resistance to yellowing in light and heat, even at high temperature
- In baking enamels very high gloss and very good gloss retention
- Excellent hardness and flexibility
- Good adhesion on steel, very good chemical resistance
- Air drying systems with excellent build and color retention

APPLICATIONS

- White and light-colored high-quality baking enamels for motor cars, washing machines, refrigerators and kitchen equipment
- Two component polyurethane lacquers
- Automotive paints in air drying car refinish paints

PHYSICAL CONSTANTS

Solid % (120°C / 3 hr)	70 ± 2
Appearance	Clear
Colour on Gardner scale	5 max
Acid Value (On Solid) (mg KOH/gm)	8-15
Viscosity in sec (of 50% solution in o-xylene at 30°C in FcB4 cup)	100-125



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

SOLUBILITY

Mix Xylene	Soluble
Butyl Acetate	Soluble
N-Butanol	Insoluble
Toluene	Soluble
MTO / W.S.	Insoluble

COMPATIBILITY

MACRO POL PB-260 (100%)	Compatible
MF Resin	Compatible
MACOXY ESTER 3560 (60%)	Partial Compatible
MACRO POL MRGLY (100%)	Compatible

DELIVERY FORM

MACRKYD F-4038	70 ± 2% in Mix Xylene
----------------	-----------------------

SHELF LIFE

1 Year*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006