

MACRKYD CA-3045

Medium Oil Pentaerythritol Esterified Alkyd Resin, modified with Castor Oil

PRINCIPAL PROPERTIES

- Non-drying alkyd

APPLICATIONS

- Nitro Cellulose polishing lacquers for furniture, Nitro Cellulose base putty and leather lacquers
- For baking

PHYSICAL CONSTANTS

Solid % (120°C / 3 hr)	60 ± 2
Appearance	Clear
Colour on Gardner Scale	4 max
Acid Value (On Solid) (mg KOH/gm)	15 max
Viscosity in sec (of 50% solution in o-xylene at 30° C in FcB4 cup)	100-125

SOLUBILITY

Mix Xylene	Soluble
Butyl Acetate	Soluble
N-Butanol	Partial Soluble
Toluene	Soluble
MTO / W.S.	Partial Soluble

COMPATIBILITY**MACRO POLYMERS PVT. LTD.**165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

MACRO POL PB-260 (100%)	Compatible
UF Resin	Compatible
MF Resin	Compatible
MACOXY ESTER 3560 (60%)	Compatible
MACRO POL MRGLY (100%)	Compatible

DELIVERY FORM

MACRKYD CA-3045	60 ± 2% in Mix Xylene
-----------------	-----------------------

SHELF LIFE

1 Year*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006