

## MACRKYD MFAP

Medium for Aluminium Paint

### PRINCIPAL PROPERTIES

- Compatibility with drying oils and long oil alkyds
- Very low acid value

### APPLICATIONS

- Very useful as medium for single pack aluminum paints

### PHYSICAL CONSTANTS

Solid % (120°C / 3 hr)	70 ± 2
Appearance	Clear
Colour on Gardner scale	12 max
Acid Value (On Solid) (mg KOH/gm)	5 max
Viscosity in sec (of 50% solution in MTO (aniline point - 47) at 30°C in FcB4 cup)	17-20

### SOLUBILITY

Mix Xylene	Soluble
Butyl Acetate	Soluble
N-Butanol	Insoluble
Toluene	Soluble
MTO / W.S.	Soluble



#### MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933  
Website : [www.macropolymers.com](http://www.macropolymers.com)

CIN : U17119GJ1994PTC024006

## COMPATIBILITY

MACRO POL PB-260 (100%)	Compatible
UF Resin	Compatible
MF Resin	Compatible
MACOXY ESTER 3560 (60%)	Compatible
MACRO POL MRGLY (100%)	Compatible

## DELIVERY FORM

MACRKYD MFAP	70 ± 2% in MTO / W.S.
--------------	-----------------------

## SHELF LIFE

1 Year*
---------

\*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.



### MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : [www.macropolymers.com](http://www.macropolymers.com)

CIN : U17119GJ1994PTC024006