

## MACRKYD D-2050 R

Medium Oil Pentaerythritol Esterified Alkyd Resin modified with Dehydrated Castor Oil and Rosin

### PRINCIPAL PROPERTIES

- Good brush ability
- Semi drying properties
- Good durability
- Very good initial gloss
- Air drying

### APPLICATIONS

- Decorative enamels in pastel shades for interior and exterior use and under coats
- For primer

### PHYSICAL CONSTANTS

Solid % (120°C / 3 hr)	50 ± 2
Appearance	Clear
Colour on Gardner Scale	10 max
Acid Value (On Solid) (mg KOH/gm)	5-20
Viscosity in sec (of 40% solution in MTO aniline point – 47 at 30° C in FcB4 cup)	170-210

### SOLUBILITY

Mix Xylene	Soluble
MTO / W.S.	Partial Soluble
Toluene	Soluble
N-Butanol	Partial Soluble
Butyl Acetate	Soluble



#### MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933  
Website : [www.macropolymers.com](http://www.macropolymers.com)

CIN : U17119GJ1994PTC024006

## COMPATIBILITY

MACRO POL MRGLY (100%)	Compatible
MACRO POL PB-260 (100%)	Compatible
UF Resin	Compatible
MF Resin	Compatible
MACOXY ESTER 3560 (60%)	Partial Compatible

## DELIVERY FORM

MACRKYD D-2050 R	50 ± 2% in MTO / W.S.
------------------	-----------------------

## SHELF LIFE

2 Years*
----------

\*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.



### MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : [www.macropolymers.com](http://www.macropolymers.com)

CIN : U17119GJ1994PTC024006