

MACRO POL MRGLY

Rosin Modified Maleic Glycerine Ester

PRINCIPAL PROPERTIES

- Compatibility with nitro cellulose, drying and non drying alkyds dissolved in aromatic solvents
- Very high gloss
- Excellent build in air drying industrial finishes
- Rapid drying resin

APPLICATIONS

- Pale coloured varnishes for industrial use
- NC system
- Auto refinish

PHYSICAL CONSTANTS

Appearance	Slight tone to clear
Colour on Gardner scale (50% solution in toluene)	12 max
Acid Value (on solid) mg KOH / gm	18-25
Viscosity in sec (of 50% solution in toluene at 30 ° C in FcB4 cup)	22-28
Melting Point (° C)	94-110

SOLUBILITY

N-Butanol	Partial Soluble
Butyl Acetate	Soluble



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

COMPATIBILITY

NC Solution	Compatible
-------------	------------

DELIVERY FORM

MACRO POL MRGLY	100%
-----------------	------

SHELF LIFE

2 Years*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.

**MACRO POLYMERS PVT. LTD.**

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006