

MACESTER P-9006

Saturated polyester resin

PRINCIPAL PROPERTIES

- Excellent flexibility & adhesion
- Very good gloss & gloss retention
- Excellent flow & leveling

APPLICATIONS

- Highly recommended for Automotive base coat & primers

PHYSICAL CONSTANTS

Solid % (120°C / 3 hr)	65 ± 2
Appearance	Clear
Colour on Gardner Scale	2 max
Acid Value (On Solid) (mg KOH/gm)	2-8
Viscosity in poise (as such at 25°C in B.F. RVT S.S.A. Spindel - 28 / RPM-100)	15-21
Hydroxyl Value (On Solid) (mg KOH/gm)	70-100

SOLUBILITY

Mix Xylene	Partial Soluble
Toluene	Partial Soluble
N-Butanol	Insoluble
Butyl Acetate	Soluble



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

COMPATIBILITY

MF Resin	Partial Compatible
UF Resin	Compatible
Short Oil Alkyd Resin	Compatible

DELIVERY FORM

MACESTER P-9006	65 ± 2% in Mix Xylene , Butyl Cellosolve
-----------------	--

SHELF LIFE

2 Years*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006