

MACESTER P-9009

Saturated polyester resin

PRINCIPAL PROPERTIES

- Excellent stain resistance
- Hydrolytic stability
- Excellent QUV resistance
- Excellent flow and leveling
- Good gloss & retention

APPLICATIONS

- Top coat for Automotive
- 2K PU for wood
- Chemical resistance coating

PHYSICAL CONSTANTS

Solid % (130°C / 30 min)	72 ± 2
Appearance	Clear
Colour on Gardner Scale	2 max
Acid Value (On Solid) (mg KOH/gm)	1-12
Viscosity in poise (as such at 25°C in B.F. RVDVE Spindle-15 / RPM-100)	40-65
Hydroxyl Value (On Solid) (mg KOH/gm)	95-105

**MACRO POLYMERS PVT. LTD.**

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

SOLUBILITY

Mix Xylene	Soluble
Toluene	Partial Soluble
N-Butanol	Soluble
Butyl Acetate	Soluble

COMPATIBILITY

MF Resin	Partial Compatible
UF Resin	Compatible
Short Oil Alkyd Resin	Compatible

DELIVERY FORM

MACESTER P-9009	72 ± 2% in Mix Xylene / C-9
-----------------	-----------------------------

SHELF LIFE

2 Years*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com
CIN : U17119GJ1994PTC024006