

MACESTER POLYOL-280

Saturated polyester resin

PRINCIPAL PROPERTIES

- Fast drying
- Good adhesion

APPLICATIONS

- Economical 2K PU for wood and metal

PHYSICAL CONSTANTS

Solid % (120°C / 3 hr)	70 ± 2
Appearance	Clear
Colour on Gardner scale	4 max
Acid Value (On Solid) (mg KOH/gm)	8-15
Viscosity in sec (50% solution in o-xylene at 30°C in FcB4 cup)	170-210
Hydroxyl Value (On Solid) (mg KOH/gm)	75-85

SOLUBILITY

Mix Xylene	Soluble
Butyl Acetate	Soluble
N-Butanol	Partial Soluble
Toluene	Soluble



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933
Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006

COMPATIBILITY

Short Oil Alkyd Resin	Compatible
UF Resin	Compatible
MF Resin	Compatible

DELIVERY FORM

MACESTER POLYOL-280	70 ± 2% in Mix Xylene
---------------------	-----------------------

SHELF LIFE

2 Years*

*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.



MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : www.macropolymers.com

CIN : U17119GJ1994PTC024006