

## MACESTER POLYOL-32

Saturated polyester resin

### PRINCIPAL PROPERTIES

- Fast drying
- Non-yellowing

### APPLICATIONS

- Economical 2K PU for wood and metal

### PHYSICAL CONSTANTS

Solid % (120°C / 3 hr)	70 ± 2
Appearance	Clear
Colour on Gardner scale	3 max
Acid Value (On Solid) (mg KOH/gm)	5-12
Viscosity in sec (in 50% Solution in O-Xylene at 30°C in FcB4 cup)	250-300
Hydroxyl Value (On Solid) (mg KOH/gm)	135-145

### SOLUBILITY

Mix Xylene	Soluble
Toluene	Soluble
N-Butanol	Insoluble
Butyl Acetate	Soluble



#### MACRO POLYMERS PVT. LTD.

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933  
Website : [www.macropolymers.com](http://www.macropolymers.com)

CIN : U17119GJ1994PTC024006

**COMPATIBILITY**

Short oil alkyd Resin	Compatible
UF Resin	Compatible
MF Resin	Not Compatible

**DELIVERY FORM**

MACESTER POLYOL-32	70 ± 2% in Mix Xylene
--------------------	-----------------------

**SHELF LIFE**

2 Years*
----------

\*Material should be stored in the original unopened containers under the shaded area at ambient temperature. Once opened and material used partially, after use the container must be properly sealed to avoid water and air contamination.

**MACRO POLYMERS PVT. LTD.**

165, Mahagujarat Ind. Estate, Sarkhej-Bavla Road, P.O. Moraiya,  
Tal. Sanand, Dist.: Ahmedabad-382213. Phone : + 91 7600060933

Website : [www.macropolymers.com](http://www.macropolymers.com)

CIN : U17119GJ1994PTC024006